The application was originally made under the Patent Cooperation Treaty with the Soviet Union Patent Office acting as the receiving office on (86) 19 Jun 1980, being given an application number PCT/SU80/00104. The application was searched by the Soviet Union Patent Office acting as the International Search Authority (ISA), and published by the International Bureau on (87) 14 May 1981 under serial number WO81/01290 in the Russian language. The text thereof.

(12) UK Patent Application (19) GB (11) 2 114 578 A

(21) Application No 8120002

(22) Date of filing 19 Jun 1980

(30) Priority data (31) 2831351

2912552

2912551 (32) 6 Nov 1979 28 Feb 1980 28 Feb 1980

(33) Soviet Union (SU)

(43) Date of issue 24 Aug 1983

(51) INT CL³ (AS GIVEN BY ISA) C08F 220/56 C08L 33/26

(52) Domestic classification C3L DF C3P JG C3W 210 227 C3Y B370 E300 U1S 1040 1064 1068 1336 C3L C3P

(56) Documents cited by ISA GB A 1288438 GB A 1319751 US A 3046201

SU A 659619
(58) Field of search by ISA
INT CP
COSE 220/56
COSL 33/26
C12K 1/06
INT CI COS 15/02
COSE 29/00
German 39c 25/01
US-195-100
260-89.7
526-307
GB.2(6) P
C3P
C6F FR group 14 class 5

CA 400 401 402

8 CH 37h AT 39-6 12

(71) Applicant
Kievsky Meditsinsky
Institut Imeni
Akademika A
A Bogomoltsa (USSR)
252004 Kiev
br Shevchenko d 13

(72) Inventors Vladimir Vladisłavovich Gashinsky Ivan Petrovich Bilko Anatoly Mikhailovich Sokolyuk

USSR

(74) Agent and/or Address for Service Mathisen Macara and Co Lyon House Lyon Road Harrow Middlesex HA1 2ET

(54) Polyacrylamide gel for medical and biological application and method of its preparation

(57) A polyacrylamide gel for medical and biological application contains polyacrylamide and physiological solution with the following ratio of components (in % by weight):

polyacrylamide 3.0-28.0 physiological solution 72.0-97.0

The method of preparation of the said polyacrylamide gel comprises polymerization of acrylamide together with methylene-bis-acrylamide and elution of the final product, both polymerization and elution be-

ing carried out in the medium of the physiological solution. The polyacrylamide gel can be used as a base of nutrient mediums for growing microorganisms, artificial crystalline lenses and elastic contact lenses.